

# BLENDA<sup>®</sup> -POX AS

Art. 534 / 3 / 0223

## 2K epoxy lacquer antistatic WV-534

VFL  
Vismara Farbladen



### Properties

BLENDA<sup>®</sup>-POX AS is an air-drying, cold-curing 2-component paint on an epoxy resin basis. BLENDA<sup>®</sup>-POX AS meets the highest standards of hygiene, durability and abrasion resistance and offers excellent resistance to a wide range of chemicals, mineral oils, fuels, diluted acids and alkalis, lime solutions, etc. BLENDA<sup>®</sup>-POX AS is non-flammable, low-odour and pleasant to work with.

### Field of application

For walls and floors, which must have antistatic properties.

### Pretreatment

For new floors, the drying and setting times must be observed according to the floor manufacturer's instructions. The substrate must be freed from all adhesion-reducing layers and impurities. For example, cement residue, sintered layers, liquid foils (curing), etc. must be completely removed by blasting, grinding (with NEUTRASOL cement floor cleaner) or other suitable means. Clean old coatings with GEIGER SE-1 leachers / PUROL active cleaner concentrate, rinse with clean water and allow to dry well. Remove poorly adhering old coats (adhesive tension test, cross-cut) mechanically.

### Processing

During application, a minimum substrate temperature of 10 °C, a maximum floor moisture of 5 % and a maximum air humidity of 75 % must be observed, otherwise film formation may be disturbed, resulting in poor drying, reduced adhesion, lower gloss, poor flow or poorer resistance. The adhesion of the coatings is also excellent on slightly damp substrates. When mixing the A and B components together, ensure that they are mixed particularly thoroughly (agitator).

### System structure

The coating must be earthed in order for the antistatic properties of the coating to take effect. To achieve a constant discharge capacity, it is recommended to install additional self-adhesive copper tapes (4590 3M copper strip).

1 x BLENDA<sup>®</sup>-XIM floor impregnation primer colourless or BLENDA<sup>®</sup>-POX 2K epoxy sealer WV-362 colourless (for absorbent surfaces)

2 x BLENDA<sup>®</sup>-POX AS 2K epoxy lacquer antistatic WV-534 diluted with 0–10 % water

To reduce the susceptibility to dirt (depending on the colour shade), an optional anti-static final sealant can be applied.

1 x BLENDA-FLOR AS 2K-PU sealing ink antistatic WV-546 colourless

### Drying

- ◆ Dust dry after about 8 hours
- ◆ Can be walked on and painted over after about 12 hours
- ◆ Fully dried after about 36 hours
- ◆ Chemical resistance and full load after approx. 7 days
- ◆ Final hardness after approx. 14 days  
(depending on the temperature, application quantity, humidity and air circulation)

### Dilution


Water.

### Extensiveness

4–5 m<sup>2</sup> per kg per application, depending on the quantity applied and the condition of the substrate.



Farben



Knuchel

High quality - Top finish

<b>Mixing ratio</b>	6,5 parts by weight component A and 1 part by weight component B (6,5 : 1).
<b>Pot life</b>	<p>After mixing the A and B components, BLENDA<sup>®</sup>-POX AS can be processed for 2–3 hours at 20 °C. Mixing units should therefore not be too large. Mixed material that becomes musty in the processing phase may no longer be used.</p> <p>Mixed residual inks must never be stored in a closed container until they have completely hardened. The product continues to react and will put the container under pressure and may cause it to burst.</p>
<b>Application</b>	<p>Scooter and brush.</p> <p>In order to achieve optimum results, it is very important to use the right tools – see KNUCHEL GUIDE on brush and roller qualities. You will find this guide both in the catalogue and on the homepage as an attachment to this product.</p>
<b>Cleaning</b>	Clean tools immediately after use with warm water, soap and brush cleaner. Thoroughly clean skin areas that have come into contact with paint with warm soapy water.
<b>Delivery form</b>	Packages (including hardener) of 7,5 kg.
<b>Shelf life</b>	<p>Components A: BLENDA<sup>®</sup>-POX AS can be stored for up to 12 months in unopened original containers. Store in a cool but frost-free place. Diluted material reduces the shelf life, depending on the degree of dilution and water quality.</p> <p>Components B: The hardener can be stored for at least 12 months in well-sealed original containers. Store in a cool but frost-free place.</p>
<b>Conductivity</b>	103 to 107 Ohm/cm
<b>Viscosity</b>	Slightly thixotropic / 150–400 mPa.s
<b>Density</b>	<p>Components A: 1,50 ± 0,05 g/cm<sup>3</sup></p> <p>Components B: 1,00 ± 0,05 g/cm<sup>3</sup></p>
<b>Solid content</b>	<p>Components A: 54 ± 1 %</p> <p>Components B: 88 ± 1 %</p>
<b>Binder base</b>	Water emulsifiable epoxy resins and amine hardeners.
<b>Pigment base</b>	Titanium dioxide
<b>Gloss level</b>	Matt
<b>Colours</b>	201 light grey and 202 medium grey
<b>Registration</b>	<p>Components A: CPID 622785</p> <p>Components B: CPID 277922 (article 966)</p>
<b>Classification</b>	For information on chemical properties and hazards as well as regulations regarding transport, processing, storage, disposal, etc., please refer to the safety data sheet.
<b>Trademark</b>	BLENDA <sup>®</sup> is a registered trademark of Knuchel Farben AG in CH-Wiedlisbach.

### Note

This leaflet is only intended as a reference and non-binding advice. The processing must be adapted to the corresponding conditions. In special cases we recommend to contact our technical service. However, all data and information on the suitability and application of the delivered products do not exempt the processor from carrying out his own tests and trials. A claim for damages for omitted, incomplete or incorrect information is excluded. This applies in particular if hardeners and other products are used in the paint build-up system.

Furthermore, we refer to our General Terms and Conditions (GTC) on our homepage.